

ROOFPROTECT RP4 WEATHERPROOF PAINT SEALANT  
MATERIAL DATA PAGE

**Viscosity, KU**

Initial	123
Heat Aged	126

**pH**

Initial	8.9
Heat Aged	8.5

**Adhesion – Dry (PLI)**

Mod. Bitumen	0.8A
Concrete Block	8.9A,C
Galvanized	2.2A
Asphalt Shingle	2.0A,C

**Adhesion – Wet (PLI)**

Mod. Bitumen	0.5A
Concrete Block	14.2C,CP
Galvanized	1.8A
Asphalt Shingle	0.6AC

**Early Blister Resistance**

16 Hour Cure, 24 Hour in water 25 mil D/D	No Blistering
---	---------------

**Salt Spray Resistance**

11 Days Salt Spray	10
--------------------	----

**Water Swelling % 24 Hour Immersion**

16.9%

**Perms**

5

**50 Hours W-O-M Elongation**

**Room Temperature**

% to Max Stress	700%
% to Break	700%
% Recovery	44%

**32 Degrees F**

% to Max Stress	430%
% to Break	430%
% Recovery	28%

**Tensile Strength, PSI**

**Room Temperature**

To Max Stress	1350
To Break	1350

**32 Degrees F**

To Max Stress	2220
To Break	2220

**Coverage # gal./sq.**

20 dry mils/100 sq. ft.	2.38(gal)
-------------------------	-----------